EN

Professionally approved products.

Datasheet

RS Assorted Adhesive Lined Heat Shrink Tubing Kit

Stock number: 417-9087

Product Specification

Mixed heat-shrink kit containing 75 pieces of flame retardant dual wall polyolefin tubing. The tubing is flexible with an inner wall of hot melt adhesive. The sleeves are supplied in a useful compartmented storage box which can be re-used. The kit can be used in many applications such as identification, insulation and protection.

Material	Dual Wall Polyolefin
Shrink Ratio	3:1
Operating Temp	-55 up to 125°C
Flammability	Flame Retardant
Min. Shrink Temp	110°C

RS, Professionally Approved Products, gives you professional quality parts across all products categories. Our range has been testified by engineers as giving comparable quality to that of the leading brands without paying a premium price.

EN

417-9087

Professionally approved products.

Datasheet

Kit Contents

Article	Diameter pre shrinkage (mm)	Diameter post shrinkage (mm)	Length (mm)	Quantity	Colour
241-7337	3.0	1.0	140	10	Red
241-7321	3.0	1.0	140	10	Blue
241-7315	3.0	1.0	140	10	Yellow
241-7359	3.0	1.0	140	10	White
241-7387	6.4	2.0	180	3	Red
241-7371	6.4	2.0	180	3	Blue
241-7365	6.4	2.0	180	3	Yellow
241-7393	6.4	2.0	180	3	White
241-7438	9.5	3.0	180	2	Red
241-7422	9.5	3.0	180	2	Blue
241-7416	9.5	3.0	180	2	Yellow
241-7444	9.5	3.0	180	2	White
241-7472	12.7	4.0	200	1	Red
241-7466	12.7	4.0	200	1	Blue
241-7450	12.7	4.0	200	1	Yellow
241-7488	12.7	4.0	200	1	White
241-7517	19.0	6.0	200	1	Red
241-7501	19.0	6.0	200	1	Blue
241-7494	19.0	6.0	200	1	Yellow
241-7523	19.0	6.0	200	1	White
241-7551	24.0	8.0	250	1	Red
241-7545	24.0	8.0	250	1	Blue
241-7539	24.0	8.0	250	1	Yellow
241-7602	40.0	13.0	250	1	Red
241-7595	40.0	13.0	250	1	Blue
241-7589	40.0	13.0	250	1	Yellow
241-7618	40.0	13.0	250	1	White

RS, Professionally Approved Products, gives you professional quality parts across all products categories. Our range has been testified by engineers as giving comparable quality to that of the leading brands without paying a premium price.

EN

417-9087

Professionally approved products.

Datasheet

Technical Properties

PHYSICAL PROPERTIES			
PROPERTY	TEST METHOD	REQUIREMENT	TYPICAL VALUE
Longitudinal Change	SAE-AMS-DTL-23053	+1% to -15%	≥ -7%
Tensile Strength	ASTM D 638	Min. 10,4 MPa	≥ 15 MPa
Elongation at Break	ASTM D 638	Min. 200%	≥ 350%
Secant Modulus	ASTM D 882	Max. 173 MPa	≤ 80 MPa

THERMAL PROPERTIES			
PROPERTY	TEST METHOD	REQUIREMENT	TYPICAL VALUE
Operating Temperature	UL 224	-55 up to 125°C	-55 up to 125°C
Min. Shrink Temperature	Shrink curve	full recovery	110°C
Heat Shock (250°C x 4h)	SAE-AMS-DTL-23053	no crack, flowing or dripping	Pass
Cold Impact (-55°C x 4h)	SAE-AMS-DTL-23053	no cracking	Pass
Corrosion of bare copper (158°C x 168h)	SAE-AMS-DTL-23053	no corrosion	Pass
Colour stability (175°C x 24h)	SAE-AMS-DTL-23053	no change	Pass

CHEMICAL PROPERTIES			
PROPERTY	TEST METHOD	REQUIREMENT	TYPICAL VALUE
Flammability	ASTM D 2671 (B)	Max. 60 seconds	Pass
Water Absorption	ASTM D 570	Max. 1,0%	≤ 0,5%
Fluid Resistance (after immersion 23°C x 24h)	SAE-AMS-DTL-23053	Min. 6,2 MPa (Tensile Strength)	Pass
Fluid Resistance (after immersion 23°C x 24h)	SAE-AMS-DTL-23053	Min. 7,9 kV/mm (Dielectric Strength)	Pass

ELECTRICAL PROPERTIES			
PROPERTY	TEST METHOD	REQUIREMENT	TYPICAL VALUE
Voltage Rating			600V
Dielectric Voltage Withstand (2.5kV x 60s)	UL 224	no breakdown	Pass
Volume Resistivity	ASTM D 876	Min. 10^{12} Ω·cm	≥ 10^{14} Ω·cm
Dielectric Strength	ASTM D 876	Min. 11,8 kV/mm	≥ 25 kV/mm

OTHER PROPERTIES			
PROPERTY	TEST METHOD	REQUIREMENT	TYPICAL VALUE
Sealing Efficiency	SAE-AMS-DTL-23053	no openings on reheat	Pass

RS, Professionally Approved Products, gives you professional quality parts across all products categories. Our range has been testified by engineers as giving comparable quality to that of the leading brands without paying a premium price.